

DENSOCRETE 555 color



2

CONCRETE REPAIR

Two-component very fine colored spread for concrete surface sealing and finalization

1. Product characteristics

Pigmented two-component composition consisting of dry inorganic based component and modified styrene-acrylate dispersion. Meets the requirements of class R3 according to EN 1504-3.

- designed for concrete repair (principle 3, 4 and 7 and method 3.1, 3.3, 4.4, 7.1 and 7.2 according to EN 1504-3)
- supplied in specified rate of components
- possibility of changing the color on black and white scale (shades of grey)
- excellent adhesion to concrete base
- permanently water-resistant
- good workability, applied manually or by spraying
- good mechanical properties
- frost-resistant

2. Use

DENSOCRETE 555 color is pigmented two-component polymer-cement mortar composition for surface repair of new monolithic reinforced concrete structures. This spread is supplied in black and white to help achieve a uniform color shade of the repaired surface and the original surface during applications where no finishing coating will be used and/or during architectural applications is this spread supplied in black and white version. By mixing black and white in different ratios it is possible to achieve various shades of grey so the repaired areas match with the original surface.

It can be also used for sealing damaged surfaces of reinforced concrete structures and also for surface unification and sealing of concrete and reinforced concrete structures repaired with **MONOCRETE** repair mortars. **DENSOCRETE 555** can be coated with any type of secondary protection in dependence on exposure of the repaired structure.

3. Physical and mechanical parameters

Requirements / results according to EN 1504-3 class R3

	Testing method	R3 Requirements	Results
Compressive strength (MPa)	EN 12190	>25	>38
Chloride Ion Content	EN 1015-7	< 0.05 %	< 0.01 %
Adhesive Bond (MPa)	EN 1542	>1.5	> 2.0
Carbonation Resistance	EN 13295	$d_k \leq$ control concrete	complies
Restrained shrinkage/expansion (MPa)	EN 12617-4	Adhesion after test ≥ 1.5	> 1.5
Elastic modulus (GPa)	EN 13415	> 15	> 15

Physical and mechanical parameters

Color	White to grey spectrum	
Bulk density of fresh spread (kg/m ³)	1 800 ± 40	
Tensile bending strength (MPa)	28 days	> 8.5
Frost resistance	> T150	

4. Test certificates

Meets the requirements of EN 1504-3, TP ŘSD Sec. 31. and TP SSBK III.

The product is certified according to Act No. 22/1997 Coll. and Regulation (EU) No 305/2011 of the European Parliament and of the Council (CPR). Continuous independent production quality control is provided by AZL 1687 LABBET®. Supervision of quality management, environmental and OSH systems is performed by Certification Body No. 3029.

5. Instruction for preparation and application

During the processing of dry mortar mixes **DENSOCRETE 555** it is generally necessary to comply with the principles contained in the relevant technological process **BETOSAN** for repair of reinforced concrete structures (TP No.1/06).

Base. Any incoherent, loose, weatherworn or otherwise visibly damaged concrete shall be completely removed from the repaired concrete surface before application. The concrete surface cannot be contaminated by substances negatively effecting adhesion to the base (fats, greases, oils, etc.). Tensile strength of concrete surface layers shall be 1.5 MPa at least. The base must be perfectly moistened before the application of spread. Extremely absorbent substrates can be cured with **DENSOCRETE 222** penetration agent.

Preparation of the spread DENSOCRETE 555 is prepared in a container of sufficient size by mixing both components well (preferably by electrically driven propeller agitator) in ratio: 2,5 kg of dry component, 0,4 liters of liquid component and 0,2 liters of water. A low-speed mixer with forced circulation is necessary for mixing. Consistency can be adjusted by adding up to 10% water, if needed.

DENSOCRETE 555 color	Dry component (kg)	Liquid component (liters)	Water (liters)	Thickness of applied layer (mm)	
				min.1	max.3
	5.0	0.8	0.4		

Workability. Workability of the prepared spread is 60 minutes under 20 °C and relative humidity 50-70 %. The prepared composition shall be suitably protected against desiccation.

Neither **temperature of the base** nor temperature of ambient air shall be below + 5 °C and above + 30 °C.

Spread application. It is necessary to thoroughly moisten the base (see above) before application of **DENSOCRETE 555 color** spread is applied mechanically or manually. Manual application means finning off, preferably with a notched trowel. Spread is applied one layer, whose thickness should be between 1 and 3 mm. Surfaces coated with the spread coating shall be effectively protected against direct sunshine and wind.

Surface finalization is performed right after the spread application with steel finisher or a semi-hard bristle brush.

Surface treatment. Repaired surfaces shall be properly treated immediately after completion to avoid especially direct exposure to sun, wind effect and other factors accelerating undesirable evaporation of the batch water. It is necessary to properly moisten the repaired places several times a day at least first 3 days after the repair. Use of a **DENSOCURE W** treatment agent proved well.

Tools shall be cleaned with water right after completion. Hardened spread can be removed only mechanically.

6. Specific consumption

Specific consumption of the spread amounts to 1.8 ÷ 2.0 kg/m² on 1 mm of layer thickness.

7. Packing and storage

The dry component is packed into PE buckets of 5 kg weight. The liquid component is packed into PE buckets of 0.8 l content. During transport and storage the **DENSOCRETE 555 color** dry component shall be effectively protected against moisture. The liquid component shall be protected against freezing. The shelf life of the product in original intact packing is 6 months for the dry component and 6 months for the liquid component.

After the expiration of min. shelf life, which is stated on the packaging, ingredients are not fully effective at reducing chromium VI below 2 ppm.

8. Health protection at work

No extraordinary sanitary measures are necessary while working with the two-component adhesive bridge **DENSOCRETE 555**. It is necessary to avoid particularly contamination of eyes and mucous membranes because the product (dry component) contains alkaline components. Health and labor safety rules applicable to work with cement or lime mortars are to be adhered to.

Issued MSDS meets the requirements of EC-Regulation 1907/2006, Article 31.

Because the product meets the criteria for classification as hazardous, it is necessary to provide the recipient or carriers with MSDS.

In countries where regulation REACH (par. 33.1): EU regulation on chemicals and their safe use (REACH: EC 1907/2006) is valid, professional users and distributors must be provided with following information automatically and without request:

This product is subject to Regulation (EC) No. 1907/2006 (REACH). It does not contain any substances that could be released from product under normal or reasonably foreseeable conditions of use. Therefore, there are no registration requirements for substances in articles within the meaning of Article 7.1 of the Regulation.

Based on our current knowledge, this product does not contain SVHC (substances of very high concern) from candidate list published by the European Chemicals Agency in concentrations above 0.1% (w / w).

9. Waste disposal

During disposal of contaminated packages or clearing debris from product, it is necessary to follow the Act No. 185/2001 Coll. on waste, as amended.

10. Important notice

All information mentioned above, especially advice for processing and application of our products is based on our knowledge from the development of chemical products and on years of experience with applications in practice at standard conditions, and proper storage and use. Due to the differing conditions during processing, high count of products, varying nature and modifications of base and other external influences, the procedure based on the information provided or on other written or oral recommendations, may not always ensure satisfactory working results. BETOSAN s.r.o. assumes no liability for provided advice or recommendation. The applicator must prove,



that he submitted complete information on time and in writing which is necessary for a proper detailed assessment by BETOSAN s.r.o. The applicator must test the suitability of the products for the intended application. Proprietary rights of third parties, above all, must be taken into account. All received are orders subject to our current "General sales and delivery conditions ". Please always make sure that you follow the most recent issue of the Technical Data Sheet. It is available, along with other information, at our Technical Department or at www.betosan.cz.

11. CE marking

 1301	
BETOSAN s.r.o. Na Dolinách 28, 147 00 Prague 4	
07	
2-34/072013	
EN 1504-3:2005	
DENSOCRETE 555 color Product designed to repair concrete with static function	
Compressive strength	> 38 MPa
Chloride Ion Content	< 0.01%
Adhesive Bond	> 2.0 MPa
Carbonation Resistance	complies
Restrained shrinkage/expansion	> 1.5 MPa
Elastic modulus	> 15 GPa
Dangerous substances	meets 5.4
Reaction to fire	European class A1

Technical Data Sheet No. 2-34
 Issued 1.1.2018

2

CONCRETE REPAIR

BETOSAN s.r.o., Na Dolinách 28, 147 00 Praha, Czech Republic
Bussiness and technical office Nová cesta 291/40, 140 00 Prague 4, Czech Republic
 Tel./fax.:+420 241 431 212, tel.:+420 241 431 215
 E-mail: paha@betosan.cz, www.betosan.cz