

# DENSOCURE W

## Curing agent

### 1. Product characteristics

Water-soluble spray on the basis of modified styrene-acrylate dispersion.

- significantly reduces loss of batch water
- contributes to better hardening of surface parts of cement bond materials
- enhances resistance of surface layers to effects of aggressive media (oils, oil products, inorganic salts, etc.).
- facilitates maintenance of treated floor layers
- generated film is permanently water-resistant and resistant to alkaline environment.
- applied by spraying, roller or manual coating
- supplied in optimum consistence fit for direct application; no additional dilution is needed

### 2. Use

**DENSOCURE W** is single-component water-soluble composition on the basis of modified styrene-acrylate copolymer, which is intended to reduce losses of batch water in newly laid or re-paired layers executed during repairs of reinforced concrete structures, casting and fabrication of new concrete elements and surfaces. Besides, **DENSOCURE W** is also intended for treatment of floor structures equipped with the abrasion resistant layer made of shake-ins of the **DENSOTOP** series. Application of this agent reduces loss of batch water and improves hardening of a floor surface as well as reduces absorbance and closes the porous system of floor surface layers. It enhances chemical resistance of the floor surface and facilitates its maintenance.

### 3. Physical and mechanical parameters

Colour of composition	Milky white
Colour of generated film	Transparent
Density (g/cm <sup>3</sup> )	1.02 ± 0.04
Content of water-soluble chlorides (%)	< 0.01
Drying out (untacky)	Till 2 hours

### 4. Test certificates

The product is certified according to Act No. 22/1997 Coll. and Governmental Decree No. 163/2002 Coll. Continuous independent production quality control is provided by AZL 1687 LABBET®. Supervision of quality management, environmental and OSH systems is performed by Certification Body No. 3029.

### 5. Instruction for preparation and application

Base. The base for application of the treatment spray are fresh laid or applied layers of repair materials, concretes and cement mortars and, generally, materials on cement basis. The treated surface shall not be covered by continuous water film (the surface should be dully dump). Dirt, dust and possible residues of de-stripping agents shall be also removed.

Preparation of curing agent. The curing agent is directly fit for application; no additional dilution is needed.

Neither temperature of the base nor temperature of ambient air shall be below + 5 °C and above + 30 °C.

Application of curing agent. The treatment agent **DENSOCURE W** is applied by sprayers to newly laid floors in particular. The treatment agent is applied to already hardened surfaces by mops or a roller. A brush is used for application to more articulated or small surfaces. The agent is usually applied in several layers so that total consumption of the treatment agent amounts to 120 - 150 ml/m<sup>2</sup>.

Tools and aids shall be cleaned by water immediately after completion of work.

### 6. Specific consumption

Specific consumption of the curing agent **DENSOCURE W** amounts to 120 ÷ 150 ml/m<sup>2</sup> at bases, which have usual absorbance.

### 7. Packing and storage

**DENSOCURE W** is packed into PE containers with net content 50 liters. The product must be protected against frost. Shelf life in undamaged packing is 6 months. On individual customer's request we can deliver the product in 10 liters PE containers.

### 8. Health protection at work

No extraordinary sanitary measures are necessary while working with the treatment agent **DENSOCURE W**. During application use of common personal protective equipment (mask, rubber gloves) is assumed. The product is incombustible and non-toxic (but also inedible). No organic diluents are released while working with this agent.

In case of accidental affliction of mucous membranes or skin wash thoroughly the irritated place with warmish water. After work treat the skin by a suitable reparative cream.

Issued MSDS meets the requirements of EC-Regulation 1907/2006, Article 31.

Because the product meets the criteria for classification as hazardous, it is necessary to provide the recipient or carriers with MSDS.

In countries where regulation REACH (par. 33.1): EU regulation on chemicals and their safe use (REACH: EC 1907/2006) is valid, professional users and distributors must be provided with following information automatically and without request:

*This product is subject to Regulation (EC) No. 1907/2006 (REACH). It does not contain any substances that could be released from product under normal or reasonably foreseeable conditions of use. Therefore, there are no registration requirements for substances in articles within the meaning of Article 7.1 of the Regulation.*

*Based on our current knowledge, this product does not contain SVHC (substances of very high concern) from candidate list published by the European Chemicals Agency in concentrations above 0.1% (w / w).*

## 9. Waste disposal

During disposal of contaminated packages or clearing debris from product, it is necessary to follow the Act No. 185/2001 Coll. on waste, as amended.

## 10. Important notice

All information mentioned above, especially advice for processing and application of our products is based on our knowledge from the development of chemical products and on years of experience with applications in practice at standard conditions, and proper storage and use. Due to the differing conditions during processing, high count of products, varying nature and modifications of base and other external influences, the procedure based on the information provided or on other written or oral recommendations, may not always ensure satisfactory working results. BETOSAN s.r.o. assumes no liability for provided advice or recommendation. The applicator must prove, that he submitted complete information on time and in writing which is necessary for a proper detailed assessment by BETOSAN s.r.o. The applicator must test the suitability of the products for the intended application. Proprietary rights of third parties, above all, must be taken into account. All received are orders subject to our current "General sales and delivery conditions ". Please always make sure that you follow the most recent issue of the Technical Data Sheet. It is available, along with other information, at our Technical Department or at [www.betosan.cz](http://www.betosan.cz)

Technical Data Sheet No. 2-9  
Issued 1.1.2018



**BETOSAN s.r.o., Na Dolinách 28, 147 00 Praha, Czech Republic**  
**Business and technical office Nová cesta 291/40, 140 00 Prague 4, Czech Republic**  
 Tel./fax.:+420 241 431 212, tel.:+420 241 431 215  
 E-mail: [paha@betosan.cz](mailto:paha@betosan.cz), [www.betosan.cz](http://www.betosan.cz)

