

# WODAFLEX KP

## Primer

### 1. Product characteristics

**WODAFLEX KP** is a primer coating enhancing the adhesion of the **WODAFLEX LQ/TH** spread system

- supplied as single-component
- ready for direct application
- perfect adhesion
- high ability to penetrate the surface

### 2. Use

**WODAFLEX KP** primer coating enhances the adhesion of **WODAFLEX LQ/TH** spread system to bases soiled with asphalt, bitumen or tar. It is also suitable to use it when applying the **WODAFLEX LQ/TH** spread system on asphalt strips or very absorbent bases.

### 3. Physical and mechanical parameters

Base	polyurethane
Color	reddish brown
Bulk density	1.2 kg/dm <sup>3</sup>

### 4. Test certificates

The product is certified according to Act No. 22/1997 Coll. and Governmental Decree No. 163/2002 Coll. Continuous independent production quality control is provided by AZL 1687 LABBET®. Supervision of quality management, environmental and OSH systems is performed by Certification Body No. 3029.

### 5. Instruction for preparation and application

Treated surfaces must be cohesive, clean, dry, oil and dust-free. The spread is applied using a velour roller, while trying to prevent puddles formation. The spread should be applied evenly so all the pores are closed and the coating is well adhered with the base. Freshly applied coating must immediately evenly covered with **BETOFIL FH** quartz filler in amount of 2.5÷4 kg/m<sup>2</sup>, to ensure proper adhesion of the **WODAFLEX LQ/TH** spread system. After 8÷12 hours, the remaining unanchored filler should be removed well. Within 24 hours after the application of the **WODAFLEX KP** primer, the **WODAFLEX LQ/TH** spread system should be applied.

Neither temperature of the substrate nor temperature of ambient air shall be below + 15 °C and above + 35 °C during application.

Tools shall be cleaned right after the work is finished. Hardened material can be removed only mechanically.

### 6. Specific consumption

Specific consumption of the **WODAFLEX KP** primer amounts to ca 0.15 kg/m<sup>2</sup>.

### 7. Packing and storage

**WODAFLEX KP** is supplied in PE canisters of 3 kg. The shelf life of the product in original undamaged packing is 6 months. During transportation and storage the material must be efficiently protected against frost.

Handling **WODAFLEX KP** primer does not require any extraordinary hygienic precautions. The material doesn't contain any harmful substances. Standard hygienic precautions should be followed and gloves and protective clothing should be worn. In case of contact with skin or mucous membrane, the contaminated area should be immediately washed with a continuous stream of water. In case of accidental swallowing seek medical attention.

Issued MSDS meets the requirements of EC-Regulation 1907/2006, Article 31.

Because the product meets the criteria for classification as hazardous, it is necessary to provide the recipient or carriers with MSDS.

In countries where regulation REACH (para. 33.1): EU regulation on chemicals and their safe use (REACH: EC 1907/2006) is valid, professional users and distributors must be provided with following information automatically and without request:

*This product is subject to Regulation (EC) No. 1907/2006 (REACH). It does not contain any substances that could be released from product under normal or reasonably foreseeable conditions of use. Therefore, there are no registration requirements for substances in articles within the meaning of Article 7.1 of the Regulation.*

*Based on our current knowledge, this product does not contain SVHC (substances of very high concern) from candidate list published by the European Chemicals Agency in concentrations above 0.1% (w / w).*

### 9. Waste disposal

During disposal of contaminated packages or clearing debris from product, it is necessary to follow the Act No. 185/2001 Coll. on waste, as amended.

### 10. Important notice

All information mentioned above, especially advice for processing and application of our products, is based on our knowledge from the development of chemical products and on years of experience with applications in practice at



# 4

WATERPROOFING

BETOSAN



standard conditions, and proper storage and use. Due to the differing conditions during processing, high count of products, varying nature and modifications of base and other external influences, the procedure based on the information provided or on other written or oral recommendations, may not always ensure satisfactory working results. BETOSAN s.r.o. assumes no liability for provided advice or recommendation. The applicator must prove, that he submitted complete information on time and in writing which is necessary for a proper detailed assessment by BETOSAN s.r.o. The applicator must test the suitability of the products for the intended application. Proprietary rights of third parties, above all, must be taken into account. All received are orders subject to our current "General sales and delivery conditions ". Please always make sure that you follow the most recent issue of the Technical Data Sheet. It is available, along with other information, at our Technical Department or at [www.betosan.cz](http://www.betosan.cz)

Technical Data Sheet No. 4-27  
Issued 1.1.2018

# WATERPROOFING



**BETOSAN s.r.o., Na Dolinách 28, 147 00 Praha, Czech Republic**  
**Business and technical office Nová cesta 291/40, 140 00 Prague 4, Czech Republic**  
Tel./fax.:+420 241 431 212, tel.:+420 241 431 215  
E-mail: [paha@betosan.cz](mailto:paha@betosan.cz), [www.betosan.cz](http://www.betosan.cz)

